

an EnPro Industries company

NSF 61 Certified Multi-Swell™ (Style 3760-U)

MATERIAL PROPERTIES

Color: Blue/Off-white

Composition: Synthetic fibers with a proprietary rubber binder. Unbranded without

anti-stick coating

Fluid Services¹: Water, aliphatic hydrocarbons, oils and gasoline

Temperature², °F (°C)

Minimum: -100 (-73) Continuous Max: +400 (+205)

Pressure², Maximum, psig (bar): 500 (34.5)

P x T (max.)², psig x °F (bar x °C)

1/32 and 1/16": 150,000 (5,100) 1/8": 100,000 (3,400)

Meets Specification: NSF 61 Certified (Gaskets 1/16" thick are certified for 6" and larger

pipe. Gaskets 1/8" thick are certified for 10" and larger.)

Contact Garlock for pipe sizes less than 6".

TYPICAL PHYSICAL PROPERTIES

ASTM F36	Compressibility, range, %:	15-30	
ASTM F36	Recovery, %:	40	
ASTM F38	Creep Relaxation, %:	30	
ASTM F152	Tensile, Across Grain, psi (N/mm ²):	1000 (6.9)	
ASTM F1315	Density , lbs./ft. ³ (grams/cm ³):	85 (1.36)	
ASTM D149	Dielectric Properties, range, volts/mil.		
	Sample conditioning	<u>1/32"</u> <u>1/68"</u>	
	3 hours at 250°F:	607 385	
	96 hours at 100% Relative Humidity:		
ASTM F104	Line Call Out:	F719996B6L100M3 ⁽³⁾	

SEALING CHARACTERISTICS

	ASTM F37B Fuel A	ASTM F37B Nitrogen
Gasket Load, psi (N/mm2):	500 (3.5)	3000 (20.7)
Internal Pressure, psig (bar):	9.8 (0.7)	30 (2)
Leakage	0.15 ml/hr.	0.20 ml/hr.

IMMERSION PROPERTIES*- ASTM F146 Fluid Resistance after Five Hours

	ASTM #1 Oil	ASTM IRM #903	Distilled Water
	300°F (150°C)	300°F (150°C)	70-85°F (20-30°C)
Thickness Increase, (%)	<u>></u> 15	<75	25
Weight Increase, (%)	<30	<85	-
Tensile Loss, (%)	-	-	-

Notes:

This is a general guide and should not be the sole means of selecting or rejecting this material. ASTM test results in accordance with ASTM F-104; properties based on 1/32" (0.8mm) sheet thickness unless otherwise mentioned.

^{*} Values do not constitute specification Limits

¹ See Garlock chemical resistance guide for Multi-Swell™ 3760.

² Based on ANSI RF flanges at our preferred torque. When approaching maximum pressure, continuous operating temperature, minimum temperature or 50% of maximum PxT, consult Garlock Applications Engineering. Minimum temperature rating is conservative.

³ Third numeral 9: F36 Compressibility 15-30%. Fourth numeral 9: % Thickness Increase in IRM Oil #903 = 75% max. Fifth numeral 9: % Weight Increase in IRM Oil #903 = 85% max.