#### Advancing the Science of Sealing\*\*

# Garlock Style 9200 Premium Grade Rubber Sheet





### **Specifications**

Material:	Nitrile with proprietary nylon insert <sup>†</sup>		
Hardness (Shore A), ±5:	70		
Tensile strength:	2,000 psi (14 MPa)		
Elongation, min.:	250%		
Number of plies:	1		
Thickness:	1/16", 3/32", 1/8", 3/16", 1/4"		
Width:	48"		
Finish:	Cloth		
Temperature max.:	250°F (120°C)		
Internal pressure, max.:	250 psig (17 bar)		
P x T, max.,	20,000 (600) psig x °F (bar x °C)		

 $<sup>^{\</sup>dagger}$  Special insert completely eliminates weepage through insert.

# Garlock SEALING TECHNOLOGIES®

#### **Value and Benefits**

- Combines elasticity and extensibility of rubber with strength of fabric insert
- Nylon-reinforced nitrile rubber resists leakage
- No measurable leakage in ASTM F-37 test for nitrogen sealability
- Resists extrusion; seals at very low compres-sive stress
- Excellent replacement for cloth-inserted rubber in water applications

#### **Ideal** for

- Water Service
- Petroleum oils
- General industrial use

#### Ordering Information

Product Code	Thickness (inches)	Width (inches)	Lbs./Yard (approx.)	Yards/Roll (approx.)	Lbs./ Roll (approx.)
51920-0330	1/16	48	5.14	38	195
51920-0338	3/32	48	7.44	27	201
51920-0346	1/8	48	9.74	18	175
51920-0361	3/16	48	14.88	9	134
51920-0377	1/4	48	19.48	9	175

#### **Test Results**

Nitrogen Sealability,

0 ml/hr

ASTM F37B

Gasket load = 500 psi (3.5 N/mm²) Internal pressure = 30 psig (0.7 bar)

**Compression Set** 

50%

D-395 Method B

22 hrs. @ 212°F (100°C)

**Volume Change** 

-10% to +5%

After immersion in

ASTM #1 Oil, 70 hrs. @ 212°F (100°C)



#### **AUTHORIZED REPRESENTATIVE**

## Garlock SEALING TECHNOLOGIES\*

an EnPro Industries company

Garlock Sealing Technologies 1666 Division Street Palmyra, New York 14522 USA 1-315-597-4811 1-800-448-6688 Fax: 1-800-543-0598 1-315-597-3039

www.garlock.com

#### **WARNING:**

Properties/applications shown throughout this brochure are typical. Your specific application should not be undertaken without independent study and evaluation for suitability. For specific application recommendations consult Garlock. Failure to select the proper sealing products could result in property damage and/or serious personal injury.

Performance data published in this brochure has been developed from field testing, customer field reports and/or in-house testing.

While the utmost care has been used in compiling this brochure, we assume no responsibility for errors. Specifications subject to change without notice. This edition cancels all previous issues. Subject to change without notice.

GARLOCK is a registered trademark for packings, seals, gaskets, and other products of Garlock.

© Garlock Inc 2007. All rights reserved worldwide.

Other Garlock facilities are located in:

**Columbia, SC, USA** Phone 1.803.783.1880 Fax 1.803.783.4279

**São Paulo, Brazil** Phone 55.11.4352.6161 Fax 55.11.4352.8181

**Saint-Étienne, France** Phone 33.4.7743.5100 Fax 33.4.7743.5151

**Singapore** Phone 65.6285.9322 Fax 65.6284.5843 Houston, TX, USA Phone 1.281.459.7200 Fax 1.281.458.0502

**Sherbrooke, Canada** Phone 1.819.563.8080 Fax 1.819-563.5620

Neuss, Germany Phone 49.2131.3490 Fax 49.2131.349.222

**Shanghai, China** Phone 86.021.62789702 Fax 86.021.62787826 **Sydney, Australia** Phone 61.2.9793.2511 Fax 61.2.9793.2544

W. Yorkshire, England Phone 44.1422.313600 Fax 44.1422.313601

Mexico City, Mexico Phone 52.555.567.7011 Fax 52.555.368.0418

**Dubai, UAE** Phone 971.4.8833652 Fax 971.4.8833682